



AUSTRALIS
PAVESTONE CO

"The Foundation of Any *Great Lifestyle*"

49 Lionel Street
Naval Base
Western Australia 6165

Phone: 08 9410 0007

Fax: 08 9410 0035

info@australispavestone.com.au
www.australispavestone.com.au

Technical Specifications for the Australis Pavestone Co. Product Range

	Description	Results	Standard or Method
1.	Compressive Strength	21 MPa	AS/NZS4456.4-1997
2.	Breaking load 400x400x60mm paver	8.9kN (Modulus of rupture: 3.7MPa)	AS/NZS 4456.5-1997
3.	Slip resistance	Classification: V Very low risk of slipping when wet.	AS/NZS4586-1999
4.	Abrasion resistance	Maximum abrasion loss 5.0cm ³	AS/NZS 4456.9-1997
5.	Salt attack resistance	Minor particle disintegration after 20 cycles and excessive disintegration after 28 cycles. Complies with criterion (b) of method test	AS/NZS4456.10-1997